

3M™ Scotchkote™ Urethane Elastomer 60RG 537

Data Sheet and Application Guide

Product Description

Scotchkote Urethane Elastomer 60RG 537 has been specifically developed as a fast curing elastomeric repair system with a high degree of flexibility for rebuilding and resurfacing rubber components.

Product Features

- Properties equal to factory produced rubbers.
- Designed for application by trowel or spatula at thicknesses up to 6mm.
- Provides good cold vulcanising capabilities.
- Designed for use to repair conveyor belts, rollers, gaskets, hoses, off road tyres etc.

General Application Steps

1. Remove oil, grease and loosely adhering deposits and degraded rubber.
2. Thoroughly abrade the surface, to produce a rough fibrous finish.
3. Apply Scotchkote Urethane Elastomer 60RG 537 to the required thickness.
4. Allow to cure.
5. Visually inspect the coating for defects.
6. Repair all defects.

Properties

Property	Value
Colour	Black
Ratio	2:1 By volume 2:1 By weight
Drying & Cure times at 20°C (68°F)	
Useable life	8 mins
Initial Set	30 mins
Machining	1 hour
Full Mechanical	24 hours
Volume Solids	100%
V.O.C (As Supplied)	Nil
Film Thickness	Up to 6mm
Volume Capacity	923cc (56.3 cu ins) per kilo
Tensile Strength	6N/mm ² (900 psi) (ASTM D412)
Dielectric Strength	16KV/mm (ASTM D149)
Elongation	600% (D412)
Shore A Hardness	60 (ASTM D2240)
Tear Strength	20N/mm (150 pli) (ASTM D624)
Maximum Operating Temperature	80°C (176°F) - Dry 50°C (122°F) - Wet
Peel Adhesion (Concrete & Steel)	9kg/cm (50pli) - cohesive failure in product (ASTM D903)



Application Procedures for 3M™ Scotchkote™ Urethane Elastomer 60RG 537

Surface Preparation

All existing dirt, oil and grease should be removed and the surface wiped with 3M™ Scotchkote™ Cleaner 020. Any areas of frayed or fragmented rubber should be cut away to provide a sound repair area. Smooth surfaces, including metals, should be mechanically etched to produce a good profile, with abrasive blasting being preferred for metal substrates. Rubber surfaces are best roughened using a stiff wire brush / comb. Edges of repair areas of belts, hoses, tyres etc. should be undercut. All loose dust and particles should be blown clear of the prepared surface. On certain repairs such as gaskets and castings where one surface is not required to bond to the Scotchkote Urethane Elastomer 60RG 537, these surfaces should be treated with 3M™ Scotchkote™ Release Agent 035.

Priming

All areas to be repaired or resurfaced should be first primed with a special fast setting Scotchkote primer comprising 3M™ Scotchkote™ Urethane Elastomer Primer 075 premixed with 3M™ Scotchkote™ Urethane Elastomer 60RG 537 Primer Catalyst. The contents of the catalyst bottle should be added to the primer container immediately prior to use and the container should then be shaken to ensure complete mixing is achieved. After use the container should be resealed, taking care not to contaminate the contents. This resealed Scotchkote Urethane Elastomer 60RG 537 Primer will have a limited shelf life of up to 3 months. The primer should be applied with a soft bristled brush to give an even, but low coating thickness, taking care to avoid ponding of the primer. The primer should be allowed a minimum of 10 minutes and a maximum of 1 hour at 20°C before applying Scotchkote Urethane Elastomer 60RG 537.

Product Mixing

Scotchkote Urethane Elastomer 60RG 537 is a two component material supplied either as 125gm sachets or 0.6kg units which must be mixed together prior to use.

Handling and Safety Precautions

Read all health hazard, precautionary and first aid statements found in the Material Safety Data Sheet, and/or product label prior to handling or use.

3M and Scotchkote are trademarks of 3M Company.

Important Notice

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product which are not contained in 3M's current publications, or any contrary statements contained on your purchase order shall have no force or effect unless expressly agreed upon, in writing, by an authorised officer of 3M.

Warranty; Limited Remedy; Limited Liability.

This product will be free from defects in material and manufacture for a period of 12 months from the time of purchase. **3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF QUALITY OR FITNESS FOR A PARTICULAR PURPOSE.** If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. **Except where prohibited by law, 3M will not be liable for any loss or damage arising from this 3M product, whether indirect, special, incidental or consequential (including, but not limited to, loss of profits, business and/or goodwill) regardless of the legal theory. For the sake of clarity, nothing in this statement will be deemed to exclude or restrict 3M's liability for death or personal injury arising from its own negligence.**

A) SACHETS

- 1) Remove outer wrapper using scissors to cut off corner, taking care not to damage the inner pack.
- 2) Extract the central dividing pin which separates the two components in the sachet.
- 3) Mix the two components together by hand, squeezing the pack and kneading the mixture for 1-2 minutes. To ensure complete mixing the product must then be transferred to a mixing board as follows.
- 4) Using scissors cut off the corner of the pack to allow the mixed product to be dispensed onto a mixing board, the product should then be mixed until completely homogenous, this will normally take a further 60 seconds.

B) 600GM UNITS

Two volumes of Part A (Base) and one volume of Part B (Activator) should be measured onto a clean surface and the two components mixed thoroughly to produce a smooth streak free material.

Thorough mixing is extremely important, and once the material appears mixed, a further period of mixing should be carried out to ensure there is not unmixed material. Once mixed the material should be used within 8 minutes, at 20°C (68°F).

Application Procedures

The mixed material should be pressed firmly onto the prepared area working the product into cracks or defects on the surface. Where necessary, reinforcement tape should be bedded into the material and overlapped to provide multi-layer reinforcement. All equipment must be cleaned IMMEDIATELY after use with Scotchkote Cleaner 020.

Packaging and Storage

Supplied in 0.60kg packs and 10 x 0.125kg sachets

Use within 12 months of date of manufacture. Store in original sealed containers at temperatures between 5°C and 32°C.

Ordering Information/Customer Service

For ordering, technical and product information or to request a copy of the Material Safety Data Sheet, call +44 (0)1609 780170 or fax +44 (0)1609 783762 (Sales) or 788718 (Technical).

For emergencies, please contact +44 (0)1344 858000.



Corrosion Protection Products 3M United Kingdom plc

23 Standard Way Industrial Estate
Northallerton
North Yorkshire DL6 2XA
United Kingdom
Phone: +44 (0)1609 780170
Fax: +44 (0)1609 780438
www.3M.co.uk/scotchkote

Corrosion Protection Products 3M United Kingdom plc

3M Centre
Cain Road, Bracknell
Berkshire RG12 8HT
Phone: 01344 858000
Fax: 01344 857970
www.3M.co.uk

Please recycle. Printed in UK.
© 3M 2010. All rights reserved.
60RG 537-0811